CHIPQUIK®

SMD291NL75G

Datasheet revision 1.3 www.chipquik.com

Tack Flux No-Clean for Lead Free in Jar 75g

Product Highlights

Ideal for all rework, solder, de-solder and reflow applications Non-corrosive, non-conductive, no-clean Tack flux will not run all over PCB when applied Has a pleasant odor Excellent wetting Easily cleaned with isopropyl alcohol (IPA) Attachment of BGA spheres Soldering flip chip components

Long stencil life

Wide process window

Clear residue

Designed for Lead-Free applications

RoHS 3 and REACH compliant



Flux Type: Synthetic No-Clean (for Lead-Free applications)

Flux Classification: REL0

Flux Activation Temperature: 140°C (284°F)

Color: Light yellow to orange/brown

Packaging: Jar 75g

Shelf Life: Refrigerated >24 months, Unrefrigerated >24 months

Stencil Life

>8 hours @ 20-50% RH 22-28°C (72-82°F) >4 hours @ 50-70% RH 22-28°C (72-82°F)

Stencil Cleaning

Automated stencil cleaning systems for both stencil and misprinted boards. Manual cleaning using isopropyl alcohol (IPA).

Storage and Handling

Store refrigerated or at room temperature 3-25°C (37-77°F). Do not freeze. Allow 4 hours for flux to reach an operating temperature of 20-25°C (68-77°F) before use.

Transportation

This product has no shipping restrictions. Shipping below 0°C (32°F) or above 25°C (77°F) for normal transit times by ground or air will not impact this product's stated shelf life.

Conforms to the following Industry Standards:

J-STD-004B, Amendment 1 (Solder Fluxes):

RoHS 3 Directive (EU) 2015/863:

Yes

Yes

